



Wax

Technical Specifications

Color Code Tab.....	Purple
Maximum Print Speed	12 IPS
Film Thickness.....	4.5 Microns
Total Ribbon Thickness.....	7.5 Microns
Transmission Density	1.45
	MacBeth Scale
Ink Melting Point.....	62°C/144°F

General Purpose Wax

Added Durability

Benefits

- Prints at low heat settings
- Specially formulated backcoat protects the printhead
- Outstanding print performance on coated stocks
- Offers higher durability than most waxes on coated stocks

Recommended Stock

Coated paper tag and label stocks
Polyethylene films
Polypropylene films

What is the application?

What is the stock and how wide is it?

The ribbon should always be slightly wider than the stock

What is the level of durability?

- Scratch
- Smudging
- Chemicals
- Outdoor Exposure

What thermal printer are you using?

Get the make and model, length of current ribbon

What you need to know to quote ribbon business.

Thermal Transfer Ribbon Storage Conditions

For optimal print results, thermal transfer printing should occur in the temperature range of 41° F to 95° F at 45% to 85% relative humidity. Suggested storage conditions for up to one year duration are 23° F to 104° F at 20% to 85% relative humidity. Exposing thermal transfer ribbons to direct sunlight or moisture will cause damage to the ribbons.